

Datasheet revision 1.0

www.chipquik.com

## Stained Glass Soldering Tacky Flux - Water-Soluble 30g/30cc Syringe

**Product Highlights** 

- Lead-Free / RoHS 3 Compliant / REACH Compliant
- Water-Soluble Tacky Flux for Stained Glass Soldering
- Low viscosity
- Stays put where applied, will not run all over work piece

### **Specifications**

| Flux Type:                   | Synthetic Water-Soluble for Stained          |
|------------------------------|--|
|                              | Glass Soldering                              |
| Flux Classification:         | Water-Soluble (Residue should be             |
|                              | water-washed off after soldering,            |
|                              | use hot water 60°C+)                         |
| Flux Activation Temperature: | 140°C (284°F)                                |
| Packaging:                   | 30cc/30g Luer Lock Syringe w/ plunger & tips |
|                              |  |



# Shelf Life >24 months

### Storage and Handling

Store refrigerated or at room temperature 3-25°C (37-77°F). Do not freeze. Allow 4 hours for flux to reach an operating temperature of 20-25°C (68-77°F) before use.

### Transportation

This product has no shipping restrictions. Shipping below  $0^{\circ}C$  (32°F) or above 25°C (77°F) for normal transit times by ground or air will not impact this product's stated shelf life.